# **COADIS**<sup>™</sup>

# TECHNICAL DATA SHEET

# COADIS™ BR 85

Dispersing Agent for water-borne systems

# Non ionic dispersant

#### **TYPICAL CHARACTERISTICS**

Nature Polyethercarboxylate
Appearance Colorless to yellow liquid

Solid Content (%) 35
Active Content (%) 35
pH 8
Specific gravity 1.09
Neutralization type Sodium
Solvent Water

#### **DESCRIPTION**

Coadis™ BR 85 is an original solution for deflocculation and steric stabilization of Titanium Dioxide and of other fine high value pigments. Coadis™ BR 85 develops specific affinities for pigments and binders, bringing unique properties. Coadis™ BR 85 is derived from Coatex proprietary Bumper Technology Coadis™ BR 85 benefits: Reduce TiO2 consumption through optimized dispersion, Boost optical properties and Improve in-can stability of Alkyd Emulsion Paints while keeping high fluidity.

# **RECOMMENDED ADDITION LEVEL**

The typical dosage should be selected in the range from 0.2 to 0.5% (dry on total formulation weight)

## **STANDARD PACKAGING**

Other packaging may be available upon request

- 1000L IBC
- 220L Drum
- Bulk

# **HANDLING & STORAGE**

It should be protected from the effects of weathering and stored between 5 and 40  $^{\circ}\text{C}.$ 

Once opened, packaging should be resealed immediately after use. In these conditions, this product should be used within 12 months from delivery.

#### **HEALTH AND ENVIRONMENTAL DATA**

For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.

#### **MARKETS**

#### **Coatings & Inks**

- Architectural Coating
- Graphic Arts
- Industrial Coating
- Textile & Leather Coating

#### **KEY BENEFITS**

#### **FORMULATION**

- Easy handling
- · Ready to use
- Compatibility



#### **STORAGE**

- Floating resistance
- · Syneresis resistance
- Antisettling
- Viscosity stability



## FILM PROPERTIES

- Anticorrosion
- Hiding power/Opacity
- Gloss

#### SAFER SOLUTIONS

- APEO Free\*
- Heavy Metal Free\*
- Solvent Free\*
- \* Not intentionally added but not specifically measured (not part of product specification)

#### **PVC**

PVC Low PVC Mid PVC High



#### **SUITABLE FOR**

Inorganic pigments Organic pigments



**Headquarter: Arkema France** 420, rue d'Estienne d'Orves 92705 Colombes Cedex – France T +33 (0)1 49 00 80 80



