

COAPUR™ 2025

Solvent free liquid polyurethane thickener

HEUR Polyurethane Thickener

TYPICAL CHARACTERISTICS

Nature	Water soluble non ionic polyurethane
Appearance	Viscous whitish liquid
Solid Content (%)	25
Active Content (%)	25
pH	7
Brookfield viscosity (mPa.s)	3000
Specific gravity	1.04
Solvent	Water

DESCRIPTION

Coapur™ 2025 is a solvent and Alkyl Phenol Ethoxylate (APEO) free associative polyurethane thickener designed for water based formulations. Coapur™ 2025 can be used sole or in combination either with other polyurethane thickeners or with any type of rheology modifiers such as acrylic or cellulosic thickeners, acting at low shear rates.

Coapur™ 2025 is a pure associative thickener. It is designed to interact strongly with the blinder of the formulation, in order to control the rheology at high shear rates. Coapur™ 2025 helps to match the highest coating quality possible for water-based formulations

RECOMMENDED ADDITION LEVEL

As sole thickener in lacquers, gloss and semi-gloss dispersion paints: 0.5% to 3%, combined with a medium and/or low shear effective thickener: 0.5 to 1.5% both based on solids content.

STANDARD PACKAGING

Other packaging may be available upon request

- 1000L IBC
- 220L Drum

HANDLING & STORAGE

It should be protected from the effects of weathering; stored between 5 and 40°C and sheltered from direct sun exposure. This product can be altered by frost. Once opened, packaging should be resealed immediately after use.

To be easily pumpable, Coapur™ 2025 should be used about 20°C.

In these conditions, this product should be used within 12 months from delivery.

HEALTH AND ENVIRONMENTAL DATA

For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.

MARKET

Coatings & Inks

- Architectural Coating
- Graphic Arts
- Industrial Coating
- Textile & Leather Coating
- Traffic Paint

Adhesives & Sealants

- Packaging Adhesive
- Pressure Sensitive Adhesives

KEY BENEFITS

FORMULATION

- **Color acceptance**
- **Compatibility**
- **Easy handling**



STORAGE

- **Viscosity stability**
- **Syneresis resistance**



APPLICATION

- **Brushability**
- **Film build**
- **Rollability**



FILM PROPERTIES

- **Hiding power/Opacity**
- **Levelling**
- **Anticorrosion**



- **APEO free**

Yes

- **Bacteria resistance**

Yes

- **Heavy metal free**

Yes

- **Solvent-free**

Yes

THICKENING MECHANISM

Associative



VISCOSITY CONTRIBUTION

High Shear contribution



PVC

PVC Low



PVC Mid

