

# CRAYVALLAC® A-2201-M

High performance polyacrylate surface tension and air release modifier  
**Polyacrylate**

## TYPICAL CHARACTERISTICS

Nature	<b>Polyacrylate</b>
Appearance	<b>Clear liquid</b>
Solid Content (%)	<b>70</b>
Active Content (%)	<b>70</b>
Specific gravity	<b>0.93</b>
Solvent	<b>Xylene/n-Butanol</b>

## DESCRIPTION

CRAYVALLAC® A-2201-M is a high performance polyacrylate surface tension modifier for the control of coating surface properties. CRAYVALLAC® A-2201-M is suitable for use in a wide range of solvent based systems and applications. CRAYVALLAC® A-2201-M has been developed specifically to enhance substrate wetting and to improved leveling. As a result when compared with unadditivated coating, film defects such as craters, fisheyes, orange peel and pinholes are reduced and a superior overall appearance of the film is visible. CRAYVALLAC® A-2201-M can be used as well as an air release agent in solvent-based high solids systems applied by airless spray.

## RECOMMENDED ADDITION LEVEL

0.1-2.0% under low to medium shear

## STANDARD PACKAGING

Other packaging may be available upon request

- 180 Kg Drum

## HANDLING & STORAGE

It should be stored in the original containers in a dry place at temperatures between 5°C (41°F) and 30°C (86°F). Avoid exposure to direct sunlight or frost. In these conditions, this product should be used within 24 months from production.

## HEALTH AND ENVIRONMENTAL DATA

For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.

## MARKET

### Packaging

### Coatings & Inks

- Graphic Arts
- Industrial Coating
- Textile & Leather Coating

## KEY BENEFITS

### FORMULATION

- **Compatibility**
- **Easy handling**
- **Post addition**



### APPLICATION

- **Air release**



### FILM PROPERTIES

- **Gloss**
- **Defects reduction**
- **Levelling**



- **APEO free**
- **Bacteria resistance**
- **Heavy metal free**

**Yes**  
**Yes**  
**Yes**