

CRAYVALLAC® PA3 X 20

Pre-activated amide rheology modifier supplied in xylene
Polyamide

TYPICAL CHARACTERISTICS

Nature	Polyamide
Appearance	Off-white paste
Solid Content (%)	20
Active Content (%)	20
Specific gravity	0.88
Solvent	Xylene and Alcohol

DESCRIPTION

CRAYVALLAC® PA3 X 20 is a pre-activated amide wax supplied in a mixture of xylene and alcohols. It is a rheology modifier in paste form for post-addition to solvent-based industrial systems. The use of CRAYVALLAC® PA3 X 20 provides a very simple and direct mean of introducing shear-thinning rheology with thixotropic viscosity recovery to formulations.

RECOMMENDED ADDITION LEVEL

0.5-5% under low to medium shear dispersion

STANDARD PACKAGING

Other packaging may be available upon request

- 15 Kg Pail

HANDLING & STORAGE

It should be stored in the original containers in a dry place at temperatures between 5°C (41°F) and 30°C (86°F). Avoid exposure to direct sunlight or frost. In these conditions, this product should be used within 24 months from production.

PROCESSING INSTRUCTIONS

In order to obtain maximum efficiency from CRAYVALLAC® PA3 X 20, it is necessary to disperse this product without destroying the crystalline fibres. It is therefore preferable to incorporate CRAYVALLAC® PA3 X 20 under low to medium shear conditions over as short a time period as possible. There are two main methods by which CRAYVALLAC® PA3 X 20 can be incorporated: Post addition: When using a high-speed disperser, CRAYVALLAC® PA3 X 20 is added during the final stages of production, when the coating has been partially thinned to a viscosity of 600-800mPas (ICI cone and plate at 10000s⁻¹) and the peripheral speed reduced to approximately 4ms⁻¹. Too high a speed will result in destruction of the active fibres and reduced performance, whereas, too low a speed will result in extended incorporation times. In general, the time required for incorporation should be kept to a minimum in order to minimise damage due to overshear. Master batch preparation: A master batch can be prepared by dispersing CRAYVALLAC® PA3 X 20 in a resin and/or solvent using low to medium shear rates. This dispersion can then be added to the finished coating. Due to the multitude of formulations, processing methods and application conditions used in the field, we strongly recommend that all products containing CRAYVALLAC® PA3 X 20 be tested thoroughly to ensure suitability for their intended end use. In particular, the suitability of this product for application by hot spray, or curing in poorly ventilated areas may require additional validation. We do not recommend CRAYVALLAC® PA3 X 20 for forced cure and stoving applications.

HEALTH AND ENVIRONMENTAL DATA

For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.

MARKET

- Coatings & Inks**
 - Industrial Coating
- Adhesives & Sealants**
 - Assembly
 - Other Adhesives

KEY BENEFITS

FORMULATION

- **Ready to use**
- **Easy handling**
- **Post addition**



STORAGE

- **Antisettling**
- **In-can appearance**
- **Syneresis resistance**
- **Viscosity stability**



APPLICATION

- **Edge-coverage**
- **Sag resistance**
- **Sprayability**



FILM PROPERTIES

- **Gloss**
- **Levelling**
- **Pigment orientation**



- **APEO free** **Yes**
- **Bacteria resistance** **Yes**
- **Heavy metal free** **Yes**

THICKENING MECHANISM

Non Associative

VISCOSITY CONTRIBUTION

Low Shear contribution