# **ECODIS**<sup>™</sup>

# TECHNICAL DATA SHEET

# ECODIS™ 345

Dispersing agent for water-borne traffic paints

# Ionic Homopolymer dispersant

# **TYPICAL CHARACTERISTICS**

Nature Polyacrylate sodium salt
Appearance Pale yellow liquid

Solid Content (%)
Active Content (%)
45

BH
Specific gravity
1.33
Neutralization type
Solvent
Solvent
45

45

45

45

Solid Content (%)
45

Solid Content

# **DESCRIPTION**

Ecodis™ 345 has been especially designed to quickly and efficiently disperse the pigments and fillers commonly utilized in waterborne traffic paints.Ecodis™ 345 ensures excellent heat age and viscosity stability.

# **RECOMMENDED ADDITION LEVEL**

The required amount varies from 0.15% to 0.5% of active ingredients based on the total weight of paint formulations. It is recommended to disperse the pigments and fillers in a pH range between 8.5 and 9.5.

#### STANDARD PACKAGING

Other packaging may be available upon request

- 1000L IBC
- 220L Drum
- Bulk

# **HANDLING & STORAGE**

It should be protected from the effects of weathering and stored between 5 and  $40^{\circ}\text{C}$ .

Once opened, packaging should be resealed immediately after use. In these conditions, this product should be used within 12 months from delivery.

# **PROCESSING INSTRUCTIONS**

Ecodis™ 345 should be used during the pigment grind and so should be added to water before the incorporation of the pigments and fillers.

# **HEALTH AND ENVIRONMENTAL DATA**

For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.

# **MARKETS**

#### **Coatings & Inks**

Traffic Paint

# **KEY BENEFITS**

# **FORMULATION**

- Cost in use
- Easy handling
- Ready to use

#### **STORAGE**

- Antisettling
- Viscosity stability
- Floating resistance
- Syneresis resistance

#### FILM PROPERTIES

Hiding power/Opacity

# ••••

••••

#### SAFER SOLUTIONS

- APEO Free\*
- Heavy Metal Free\*
- Solvent Free\*
- \* Not intentionally added but not specifically measured (not part of product specification)

# **PVC**

PVC Low PVC Mid PVC High



# **SUITABLE FOR**

Fillers

Inorganic pigments Organic pigments



**Headquarter: Arkema France** 51, Esplanade du Général de Gaulle 92800 Puteaux – France T +33 (0)1 49 00 80 80

