

TECHNICAL DATA SHEET

RHEOCOAT™ 27 C

Thickener and water retention agent for paper & board coating

TYPICAL CHARACTERISTICS

Nature	Acrylic copolymer in aqueous dispersion
Appearance	Milky white liquid
Solid Content (%)	30
pH	5
Brookfield viscosity (mPa.s)	150
Specific gravity	1.07

DESCRIPTION

Rheocoat™ 27 C helps to keep your process under control. Rheocoat™ 27 C is a synthetic rheology modifier allowing a better control of the coating process and an improved paper and board qualities. Rheocoat™ 27 C is a pre-neutralized emulsion, ready to use and easy to mix into the coating colors. Rheocoat™ 27 C provides an outstanding water retention with a moderate thickening effect.

RECOMMENDED ADDITION LEVEL

0.2 to 0.5 parts d/d

STANDARD PACKAGING

Other packaging may be available upon request

- 1000L IBC
- Bulk

HANDLING & STORAGE

All pipes and tanks shall be in stainless steel or any corrosion resistant material. The product is a concentrated dispersion. To prevent the formation of a dried film it is strongly advised to avoid prolonged contact to air in the system, storage and valves. The product can be irreversibly altered by frost. It should be protected from the effects of weathering and stored between 5 and 40°C and protected from direct sun exposure. In these conditions, this product should be used within 6 months from delivery.

PROCESSING INSTRUCTIONS

Shall be introduced at the end of the coating color preparation after the pigments and the binders and prior to the pH adjustment with a diluted caustic soda.

HEALTH AND ENVIRONMENTAL DATA


For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.

MARKETS

- Pulp & Paper**
- Board Coating
 - Board Coating
 - Paper Coating
 - Paper Coating

KEY BENEFITS

- Precoat
- Topcoat
- Water retention
- Anti-clogging



Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80