

## TECHNICAL DATA SHEET

# RHEOCOAT™ 93 NA

Thickener and water retention agent for paper & board coating

### TYPICAL CHARACTERISTICS

Nature	<b>Acrylic copolymer in aqueous dispersion</b>
Appearance	<b>White liquid</b>
Solid Content (%)	<b>30</b>
pH	<b>5</b>
Brookfield viscosity (mPa.s)	<b>150</b>
Specific gravity	<b>1.06</b>

### DESCRIPTION

Rheocoat™ 93 NA helps to keep your process under control. Rheocoat™ 93 NA is a synthetic rheology modifier allowing a better control of the coating process and an improved paper and board qualities. Rheocoat™ 93 NA is a pre-neutralized emulsion, ready to use and easy to mix into the coating colors. Rheocoat™ 93 NA provides good water retention with an outstanding thickening effect.

### RECOMMENDED ADDITION LEVEL

0.05 to 0.4 parts d/d

### STANDARD PACKAGING

Other packaging may be available upon request

- 1000L IBC
- Bulk

### HANDLING & STORAGE

The product can be irreversibly altered by frost. It should be protected from the effects of weathering and stored between 5 and 40°C and protected from direct sun exposure. In these conditions, this product should be used within 6 months from delivery.

### PROCESSING INSTRUCTIONS

Shall be introduced at the end of the coating color preparation after the pigments and the binders and prior to the pH adjustment with a diluted caustic soda.

### HEALTH AND ENVIRONMENTAL DATA

For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.

### MARKETS

#### Pulp & Paper

- Board Coating
  - Board Coating
- Paper Coating
  - Paper Coating

### KEY BENEFITS

- |  |     |
|--|-----|
| • Precoat                              | No  |
| • Topcoat                              | Yes |
| • Contribution to brookfield viscosity |     |
| • Anti-clogging                        |     |

**Headquarter: Arkema France**  
420, rue d'Estienne d'Orves  
92705 Colombes Cedex – France  
T +33 (0)1 49 00 80 80