

TECHNICAL DATA SHEET

TOPSPERSE™ S 50C

Good balance cost and performance

TYPICAL CHARACTERISTICS

Nature	Polycarboxylate in aqueous solution
Appearance	Brown liquid
Solid Content (%)	50
pH	8
Specific gravity	1.295

DESCRIPTION

TOPSPERSE™ S 50C, has been developed due to several advantages over multiple benefits. Higher concentration: 50% vs 42% - Lower viscosities at low temperatures, even pumpable at -5°C without heating - Easy to use with higher operating window - Contribute to aggregates reduction

RECOMMENDED ADDITION LEVEL

0.025 to 0.3 d/d

STANDARD PACKAGING

Other packaging may be available upon request

- 1000L IBC
- Bulk

HANDLING & STORAGE

Once opened, packaging should be resealed immediately after use. The product should be protected from the effects of weathering, stored between 5 and 40°C and protected from sun exposure. In these conditions, this product should be used within 12 months from delivery.

PROCESSING INSTRUCTIONS

Shall be introduced at the end of the coating color preparation after the pigments and the binders and prior to the pH adjustment with a diluted caustic soda.

HEALTH AND ENVIRONMENTAL DATA

For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.

MARKETS

Pulp & Paper

- Board Coating
- Board Coating

KEY BENEFITS

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80