

VISCOATEX™ 560

Acrylic thickener for water-based systems
ASE Acrylic Thickener

TYPICAL CHARACTERISTICS

Nature	Aqueous dispersion of an acrylic copolymer
Appearance	Low viscous white milky liquid
Solid Content (%)	28
Active Content (%)	28
pH	3.2
Specific gravity	1.04
Solvent	Water

DESCRIPTION

VISCOATEX™ 560 is a formaldehyde-free, APEO-free , Heavy metal-free and Solvent-free non associative thickener designed for use in adhesives, paints, sealants and mastics. VISCOATEX™ 560 imparts robustness versus variations of ingredients such as latex type, surfactant and co-solvent.

RECOMMENDED ADDITION LEVEL

0.1 - 1.5 % as supplied based on total formulation weight.

STANDARD PACKAGING

Other packaging may be available upon request

- 1000L IBC
- 220L Drum
- Bulk

HANDLING & STORAGE

It can be irreversibly altered by frost. It should be protected from the effects of weathering, stored between 5 and 40°C and protected from direct sun exposure. Once opened, packaging should be resealed immediately after use. In these conditions, this product should be used within 6 months from delivery.

PROCESSING INSTRUCTIONS

Supplied as a low viscosity liquid emulsion, VISCOATEX™ 560 is very easy to handle. VISCOATEX™ 560 may be used either at the beginning of the formulation or in the pigment grinding or in the finished product to adjust the final viscosity. The pH of the formulated product must be controlled to obtain good performance and reproducible viscosity. Film-forming product, surface may dry in contact with air. If necessary, filter the product prior its use.

HEALTH AND ENVIRONMENTAL DATA

For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.

MARKET

- Coatings & Inks**
- Architectural Coating
 - Graphic Arts
 - Industrial Coating
 - Textile & Leather Coating

- Adhesives & Sealants**
- Assembly
 - Other Adhesives
 - Sealants

KEY BENEFITS


FORMULATION

- **Cost in use**
- **Easy handling**
- **Color acceptance**



STORAGE

- **Syneresis resistance**
- **Antisettling**
- **In-can appearance**
- **Viscosity stability**



APPLICATION

- **Brushability**
- **Rollability**
- **Sag resistance**



FILM PROPERTIES

- **Gloss**
- **Hiding power/Opacity**
- **Rub out**



- **APEO free** Yes
- **Bacteria resistance** Yes
- **Heavy metal free** Yes
- **Solvent-free** Yes

THICKENING MECHANISM

Non Associative A horizontal row of 10 dots. The first 8 dots are dark blue, and the last 2 dots are light blue.

VISCOSITY CONTRIBUTION

Low Shear contribution A horizontal row of 10 dots. The first 8 dots are dark blue, and the last 2 dots are light blue.

Mid Shear contribution A horizontal row of 10 dots. The first 8 dots are dark blue, and the last 2 dots are light blue.

PVC

PVC High A horizontal row of 10 dots. The first 8 dots are dark blue, and the last 2 dots are light blue.

PVC Mid A horizontal row of 10 dots. The first 8 dots are dark blue, and the last 2 dots are light blue.